



CI/SfB

(43)

Yq

JUNE 2018
PRODUCT DATA SHEET

ARDEX A 950

Multi-Purpose Renovation Compound and Lightweight High Build Repair Mortar

Features

- Polymer Modified Cementitious Lightweight Repair Mortar for Internal Use
- Slump free, apply from 2mm to 100mm
- Can receive all finishes after 24 hours, regardless of thickness
- Ideal for general building work, filling large cavities and deep holes around door frames
- Can facilitate “dot and dab” fixing of plasterboards
- Can be used as a modelling mortar, to create architectural features, such as columns and pedestals
- No priming required
- 8m² coverage at 3mm thick
- Can be tiled in as little as 90 minutes.
- Low-tension, shrinkage compensated, even in thick layers
- Non-combustible – Reaction to fire Class A1 (EN 13501-1)



RAPIDRY



Binds the mix water within the mortar, speeding drying and hardening times irrespective of application thickness



Reg No. FM 1207

EMS 565427

QHS 628374

ARDEX UK LIMITED

Homefield Road, Haverhill, Suffolk CB9 8QP UK.

Telephone: +44 (0)1440 714939

Fax: +44 (0)1440 716640

Email: technical_admin@ardex.co.uk

ARDEX online: www.ardex.co.uk

ARDEX A 950

Multi-Purpose Renovation Compound and Lightweight High Build Repair Mortar

DESCRIPTION

ARDEX A 950 is a grey multi-purpose rapid drying, deep fill renovation compound. ARDEX A 950 can reshape and repair walls and floors. ARDEX A 950 can also be used as a wall render or as a floor screed prior to tiling. Made of specialist cements, easily dispersible polymers and lightweight aggregates.

USE

Internal repairing, rendering and smoothing of floors, walls and ceiling areas, filling of large cavities, and deeper sections. ARDEX A 950 can be applied as a deep filling repair mortar which hardens after approximately one hour. The mortar is stress-free and shrinkage compensated. Ideal for:

- General building work, and filling large cavities and deep holes around door frames
- "Dot and dab" fixing of plasterboards
- Can fix plasterboard to "box in" pipework or apertures
- Use as a modelling mortar, smooth and shape before drying with stencils to create architectural features such as columns and pedestals
- Smoothing, repairing and levelling of walls.
- Can be used as a screed for flooring in dry internal areas

SUBSTRATE PREPARATION

The substrate must be dry, firm, load-bearing and free from dust, dirt and other materials likely to impair adhesion. Old, flaky or weakly adhered paints, as well as loose plaster and wall-paper, must be fully removed. Priming is rarely required.

Dense non-absorbent coverings/surfaces must be primed with ARDEX P 82 Water Based Epoxy Primer and Bonding Agent. Gypsum based substrates, such as plaster, should be primed with ARDEX P 51 Concentrated Water-Based Primer and Bonding Agent. Dilute with 3 parts water to 1 part primer, apply with a brush and allow to dry.

NOTE: Compatible primers should always be used. If there is any doubt about suitability, perform a test application.

MIXING

Approximately 7¾ litres of water is required to mix 25kg of the ARDEX A 950 Powder.

Add the powder slowly to the required amount of clean, cold water, stirring continually. The use of an ARDEX mixing

paddle with a 10mm chuck electric drill makes light work of mixing.

Clean water is placed into a clean mixing container and, whilst stirring vigorously, as much powder as is required is added to achieve a supple, lump-free, stable mortar. After a standing time of 1-3 minutes the mortar should be re-mixed. The mortar can be worked within approximately 30-40 minutes and applied immediately at the desired thickness.

APPLICATION

ARDEX A 950 can be applied to prepared substrates such as, cement/sand screeds, mature renders, concrete, particle boards, securely fixed tile backer boards, existing tiles, terrazzo, gypsum based substrates and other commonly used building materials.

In order to produce smooth surfaces, the mortar, after initial hardening, can be subsequently coated or gently rubbed down using a damp sponge and trowel to close the pores, and, if necessary carved/ shaped with a steel float, before it fully dries to create a smooth flush finish with the surrounding background. ARDEX A 950 must be worked and applied at temperatures above 5°C.

DRYING TIMES

Thin layers will be dry in as little as 90 minutes and can receive a painted finish. Thicker layers up to 100mm will be dry usually in 24 hours in good conditions.

Higher temperatures shorten and lower temperatures extend the setting time.

COVERAGE

Approximately 8m² at 3mm thick.

PACKAGING

ARDEX A 950 Powder is packaged in paper sacks incorporating a polyethylene liner – net weight 25kg.

STORAGE AND SHELF LIFE

ARDEX A 950 has a storage life of not less than 12 months if stored in dry conditions.

TECHNICAL DATA

Mixing ratio: Approx. 7¾ litres of water: 25kg powder is equivalent to approx. 1 part water to: 3 parts powder by volume

Bulk density: Approx. 1.1kg/litres

Weight of fresh mortar: Approx. 1.4kg/litres

Material requirement: Approx. 1.1kg powder per m²/mm

Working time (+20°C): Approx. 30-40 minutes

pH value of freshly mixed mortar containing cement = Approx. 12

pH value of set filling layer = Approx. 10

COMPRESSIVE STRENGTH

After 1 day Approx. 6 N/mm²
After 7 days Approx. 10 N/mm²
After 28 days Approx. 16 N/mm²

TENSILE BENDING STRENGTH

After 1 day Approx. 2 N/mm²
After 7 days Approx. 3 N/mm²
After 28 days Approx. 4 N/mm²

REACTION TO FIRE

Class A1 to EN 13501-1

NOTE: The information supplied in our literature or given by our employees is based upon extensive experience and, together with that supplied by our agents or distributors, is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations.

TECHNICAL ADVICE HELPLINE
01440 714939
ARDEX online:
www.ardex.co.uk