



CI/SfB

(43)

Yq2

MARCH 2014
PRODUCT DATA SHEET

ARDEX DS 20

Decoupling Mat

Features

- Decoupling fleece mat for the installation of tiles, slabs, natural stone and concrete pavers
- Decoupling function minimises tension between the sub-floor and installed floorcovering
- Bridges non-moving cracks up to 3mm in width
- Minimises build height – only 0.4mm thick
- Loose laid system allows the installation of new tiles and slabs without damaging the existing sub-floor
- For renovation and new construction, domestic and commercial areas with loads up to 2KN/m².
- Easy to cut and apply
- Suitable for heated screeds



Reg No. FM 01207

EMS 565427

OHS 628374

ARDEX UK LIMITED
Homefield Road, Haverhill, Suffolk CB9 8QP UK.
Telephone: +44 (0)1440 714939
Fax: +44 (0)1440 716640
Email: technical_admin@ardex.co.uk
ARDEX online: www.ardex.co.uk

ARDEX DS 20

Decoupling Mat

DESCRIPTION

ARDEX DS 20 is a decoupling layer manufactured from polyethylene, with both sides laminated with polypropylene fleece.

USE

For renovation, new construction and to decouple tiles, slabs, natural stone and concrete pavers on internal domestic and commercial floors with loads up to 2KN/m².

For the unbonded installation of tiles and slabs in domestic areas where there is a requirement to avoid damage to the existing sub-floor e.g. rental accommodation.

SUBSTRATE PREPARATION

The substrate must be dry, free from dust and release agents and rigid enough to support the imposed loadings from the tiles/slabs, along with any subsequent trafficking. The maximum deflection of the substrate for ceramic floor tiles should be 1/360 and for natural stone 1/720.

The surface regularity of the substrate should be to SR1 in accordance with BS 8204, so no gap is greater than 3mm under a 2m straight edge, so that a thin adhesive bed can be used. Uneven surfaces must be primed and levelled with the appropriate ARDEX primer and levelling and smoothing compound, prior to the installation of ARDEX DS 20.

ARDEX DS 20 will bridge non-moving cracks up to 3mm in width. If there are any differences in height between the cracks the area will require smoothing with the appropriate ARDEX levelling and smoothing compound before the application of ARDEX DS 20.

APPLICATION

To minimise the transmission of sound to adjacent walls, install acoustic strips along the walls prior to the application of the appropriate ARDEX levelling and smoothing compound and ARDEX DS 20. Always ensure accurate fitting of the acoustic strips.

LOOSE LAID SYSTEM

For use in rental accommodation to avoid damage to the sub-floor.

Roll out the ARDEX DS 20 sheets and cut them to the required length, touching the acoustic strips (the sheets can be held in place with double sided adhesive tape applied to the underside).

The appropriate ARDEX adhesive can then be spread onto the ARDEX DS 20 mat with a suitably sized notched trowel, stopping a minimum of 10cm from the long edge of the mat.

The second sheet can then be pushed below the exposed edge of the first sheet, ensuring an overlapping edge of a minimum of 5-10cm, and the appropriate ARDEX adhesive applied. The subsequent sheets can then be applied as above.

BONDED SYSTEM FOR DECOUPLING

If necessary the sub-floor should be primed and allowed to dry.

Roll out the ARDEX DS 20 and cut roughly to size, peel back the rolls and apply the ARDEX adhesive to the substrate, (see list below) roll back and lay the prepared ARDEX DS 20 sheet into the fresh adhesive bed ensuring that it is applied within the open time of the adhesive. Ensure full adhesion between the decoupling mat and adhesive by smoothing the mat out with a trowel or float.

Make sure the sheets are butt jointed at the edge and not overlapped.

Installation of tiles can commence after approximately 2 hours if ARDEX X 78 S, ARDEX S 27, ARDEX S 28 or ARDEX X 7 R is used to adhere the ARDEX DS 20 sheets. If ARDEX X 78 or ARDEX X 77 are used for the installation of the DS 20 sheets, tiling can commence after 24 hours.

ARDEX AF 200 should be used for timber substrates and will allow tiling to commence after approximately 2 hours.

The adhesive used must be allowed to gain sufficient bond so the ARDEX DS 20 cannot move or deform when walked on before the installation of the chosen floor tiles.

INSTALLATION OF TILES AND SLABS ON TOP OF ARDEX DS 20

The table overleaf provides detailed information on sub-floor preparation and the appropriate use of primers and adhesives used in the installation of ARDEX DS 20.

The tiles to be installed should have a minimum size of 10 x 10cm and a minimum breaking strength of 1500 N. Ceramic floor tiles should be at least 8mm thick and natural stone should be at least 15mm thick.

We recommend the use of ARDEX X 78, or ARDEX X 78 S when installing non-moisture sensitive natural stone or concrete pavers.

To avoid staining or warping moisture sensitive natural stones should be installed using one of the ARDEX Natural Stone Adhesives (ARDEX S 27, ARDEX S 28, ARDEX X 7001 or ARDEX X 32).

The adhesive bed should be no thicker than 4mm on top of an unbonded layer of ARDEX DS 20. The adhesive bed should be no greater than 5mm on top of a bonded layer of ARDEX DS 20.

Isolated areas of suitable adhesive may be used up to thicknesses of 10mm.

The maximum bay size must not exceed 40m² with a maximum longest length of 8m. Construction and movement joints in

underlying substrates must be brought up through the final tile finish. Movement joints

should be included at room perimeters and where tiling abuts fixed objects. Tile surface movement joints should be incorporated over existing movement joints and where there is a change of level/plane etc. Further guidance is available in BS 5385.

ARDEX DS 20 is not designed to stop substantial cracks or joints transmitting through the tile bed, or cracks that result from vertical movement. Any joint or crack that is subject to movement should be either stitched with an appropriate epoxy based product, such as ARDEX EP 2000, to stabilise the joint before overlaying, or carried through the floor finish as appropriate. Apply ARDEX DS 20 at temperatures above 5°C.

If in any doubt apply a trial area.

If ARDEX DS 20 is to be used as a waterproof layer it must be bonded to the substrate as described in the table overleaf. Any cracks, joints etc. not liable to movement must be treated with ARDEX SK-12 tape. Drain or pipe outlets must be treated with ARDEX SK-W or ARDEX SK-F sealing collars.

The ARDEX sealing tapes, collars etc, should be applied/embedded into a 3mm x 3mm ribbed bed of ARDEX WPC Waterproof Protection System (Mix No. 2), smoothed flat and left to harden prior to tiling. At junctions where the wall meets the floor on adjacent walls the junction must be sealed with ARDEX SK-12 tape. Internal corners where the wall meets the wall and floor must be sealed with ARDEX SK-90 tape. External corners of a wall that abut a floor must have the junction sealed with ARDEX SK-270 tape. See photos overleaf.

TECHNICAL DATA

According to ARDEX Quality Standards:

Width of the Sheets:	Approx. 1.0m
Thickness:	Approx. 0.4mm
Weight:	Approx. 180g/m ²
Colour:	Blue
Suitable for underfloor heating:	Yes
Packaging:	50m ² per roll
Storage:	Can be stored for approx. 24 months in dry rooms.

NOTE: The information supplied in our literature or given by our employees is based upon extensive experience and, together with that supplied by our agents or distributors, is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations.

TECHNICAL ADVICE HELPLINE

01440 714939

ARDEX online: www.ardex.co.uk

ARDEX DS 20

Decoupling Mat

Substrate	As an unbonded system	Primer	Adhering ARDEX DS 20	Floor Tile Installation onto ARDEX DS 20
Sand cement screed minimum of 3 weeks old	YES		ARDEX X 78/ARDEX X 78 S, ARDEX X 77/ARDEX X 77 S, ARDEX X 7 R, ARDEX S 27, ARDEX S 28, ARDEX X 7001	ARDEX X 78/ARDEX X 78 S, ARDEX X 77/ARDEX X 77 S, ARDEX X R, ARDEX S 27, ARDEX S 28, ARDEX X 7001 as appropriate for the tile being fixed and the location *
Concrete (minimum 6 weeks)	YES		as above	as above
Gypsum based screed. moisture content maximum 0.5%	YES	ARDEX P 51 1:3	as above	as above
New mastic asphalt sand keyed surface	YES		as above	as above
smooth mastic asphalt	YES	ARDEX P 82	as above	as above
Plywood + Chipboards (min. 25 mm thick)	YES		ARDEX AF 200 ensure chipboard is free of wax etc.	as above
OSB-boards (min. 25 mm thick)	YES		NO	as above
Timber floors	YES	ARDEX P 51 Levelling with ARDEX FA 20 (if uneven)	as above	as above
PVC coverings	YES		NO	as above
Linoleum coverings	YES		NO	as above
Tiles and slabs	YES	ARDEX P 82 ARDEX P 4	as above	as above

*Please refer to the specific product datasheet for the appropriate use of the selected adhesive.

ARDEX Sealing Tapes




ARDEX SK-12
Crack bridging /
junction tape




ARDEX SK-W
120mm x 120mm
pipe collar
(Approx. 14mm
diameter hole)



ARDEX SK-F
425 x 425mm
pipe collar
(Approx. 50mm
diameter hole)



ARDEX SK-90
Internal angle
gasket



ARDEX SK-270
External angle
gasket