

Sustainability data sheet

ARDEX AM 100 Rapid Hardening One Coat Tiling Render

Specially formulated pre-blended cement/sand render, requiring only the addition of water to produce a slump free mortar which can be applied from 2 to 20mm, and is ready to receive wall tiling only 2 hours after application.

Emissions

According GEV (Gemeinschaft Emissionskontrollierte Verlegewerkstoffe, Klebstoffe und Bauprodukte e.V., Düsseldorf)

EMICODE® EC 1^{PLUS},
very low emission



According French VOC Classification

A+



solvent-free

EPD (Environmental Product Declaration)

ARDEX AM 100 corresponds to FEICA EPD:

EPD-DBC-20220217-IBF1-EN

Technical Assessment

According GISBAU (TRGS 610, Technische Regeln für Gefahrstoffe):

GISCODE ZP1 - cementitious product, low-chromate

ARDEX GmbH
Friedrich-Ebert-Straße 45
58453 Witten
www.ardex.de

Tel.: +49 2302 664-511
Fax: +49 2302 664-298
kundendienst@ardex.de
www.ardex.de



ARDEX AM 100

Rapid Hardening One Coat Tiling Render

Sustainable Building

Accordinging DGNB (Deutsche Gesellschaft für Nachhaltiges Bauen)

Version 2018

DGNB criteria ENV 1.2: Local environmental impact

ARDEX AM 100 can be classified as primers, primer coatings, putties and adhesives under wall and floor coverings (eg. Tiles, carpets, wooden floors, resilient flooring – except wallpaper).

ARDEX AM 100 has the GISOCDE ZP1 and is certified by EMICODE® EC 1^{PLUS}, very low emission, based on GEV.

ARDEX AM 100 fulfills the requirements for highest Quality Level 4.

Version 2015

DGNB criteria ENV 1.2: Local environmental impact

ARDEX AM 100 can be classified as primers, primer coatings, putties and adhesives under wall and floor coverings (eg. Tiles, carpets, wooden floors, resilient flooring – except wallpaper).

ARDEX AM 100 is certified by EMICODE® EC 1^{PLUS}, very low emission, based on GEV.

ARDEX AM 100 fulfills the requirements for highest Quality Level 4.

Accordinging LEED (Leadership in Energy and Environmental Design)

Version 4 (2014)

EQ: Low Emitting Materials

ARDEX AM 100 meets the requirements according EMICODE® EC 1^{PLUS}, very low emission, based on GEV which are accepted by LEED.

ARDEX AM 100 meets the requirements and contributes to achieving one LEED point under EQ: Low Emitting Materials.

MR: Building Product Disclosure and Optimization – Environmental Product Declaration

ARDEX AM 100 corresponds to a model EPD by FEICA, which provides the evidence of a life cycle assessment (LCA) „cradle to gate“.

ARDEX AM 100 fulfills the requirements and contributes to achieving a LEED point under MR: Building Product Disclosure and Optimization – Environmental Product Declaration.

Version 2009

IEQ Credit 4.1: Low Emitting Materials: Adhesives and Sealants

Cement based renders are not directly described by LEED. But the permitted limit value in the category coatings is 50 g/L. The VOC value of ARDEX AM 100 is < 50 g/L.

ARDEX AM 100 meets the requirements and contributes to achieving one LEED point under IEQ: Low Emitting Materials.

MR Credit 5.1 und 5.2: Regional Materials

Production site: 58453

Distance Production site – Project site < 800 km

Products that are used regionally within a 500 mile (800 kilometer) can be contributed to achieving one LEED point.

ARDEX GmbH
Friedrich-Ebert-Straße 45
58453 Witten
www.ardex.de

Tel.: +49 2302 664-511
Fax: +49 2302 664-298
kundendienst@ardex.de
www.ardex.de



ARDEX AM 100

Rapid Hardening One Coat Tiling Render

Notice: This data sheet has been compiled based on state-of-the-art technology and our experience. In spite of diligent treatment of all information ARDEX GmbH cannot guarantee the actuality or correctness of the published data. The interpretation of building certification criteria can differ and depend on the project and scope of application. The content of these data sheet does not manifest any legal relationship. Additionally, the current information given in the Technical and the Material Safety Data Sheet have to be considered.

ARDEX GmbH
Witten, 09/03/2023

ARDEX GmbH

Friedrich-Ebert-Straße 45

58453 Witten

www.ardex.de

Tel.: +49 2302 664-511

Fax: +49 2302 664-298

kundendienst@ardex.de

www.ardex.de

